

## Material 70 FKM 727

black

cross linking: peroxidic

### *Attention: preliminary datasheet*

<b>Print date</b>	<b>revision index</b>	<b>revision date</b>	<b>page</b>	1/1
6/12/2018	1	6/14/2016		

<b>Physical properties</b>	<b>nominal range</b>	<b>typical values</b>	
<b>Density</b> DIN EN ISO 1183, 23 °C	---	1.83	g/cm <sup>3</sup>
<b>Hardness</b> DIN EN ISO 7619-1, Shore A	---	73	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	3.8	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	---	21	MPa
<b>Elongation at Break</b> DIN 53504, S2, 23 °C	---	321	%
<b>Compression set</b> DIN ISO 815, B, 24 h, 200 °C, 25 %	---	19	%
<b>Temperature range</b>	-25°C to 200°C		

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Freudenberg**  
Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com



## Material 70 FKM 727

black  
cross linking: peroxidic

**Print date**  
6/12/2018

page 1/1

### Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
NSF 51	USA	Seals	food		<input checked="" type="checkbox"/>

### Freudenberg

Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com