

Material

75 Fluoroprene XP41

powder blue

cross linking: peroxidic

revision index	revision date	page	1 / 3
7	11/4/2019		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	2.00 ±0.03	2.02	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	75 ±5	77	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	5.9	MPa
Tensile strength DIN 53504, S2, 23 °C	> 18	19.5	MPa
Elongation at Break DIN 53504, S2, 23 °C	> 250	306	%
Compression set DIN ISO 815, B, 24 h, 175 °C, 25 %	< 30	23	%
Compression set DIN ISO 815, B, 24 h, 150 °C, 25 %	---	19	%
Compression set DIN ISO 815, B, 70 h, 150 °C, 25 %	---	20	%
Surface resistivity DIN EN 62631-3-1 (VDE 0307-3-1) Ausgabe 2016, 50 %, 23 °C	---	5,1 E +11	Ohm
Durchgangswiderstand 500 V, 23 °C, 50 %	---	>1,0 E +13	Ohm*cm
Temperature range	-15°C to 200°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
3-A Sanitary	USA	Seals	Class I	12 / 2021	<input type="checkbox"/>
ADI Free			see certificate		<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com



Material

75 Fluoroprene XP41

powder blue

cross linking: peroxidic

revision index

revision date

7

11/4/2019

page 2 / 3

	Country	Part	Remark	Expires	unlimited
BNIC (Cognac)	F	Seals			<input checked="" type="checkbox"/>
BPA/Phthalate free			BPA/Phthalate free		<input checked="" type="checkbox"/>
CMR Category 1A/1B free			see certificate		<input checked="" type="checkbox"/>
Decree of 21. March 1973	IT	O-Ring	food	09 / 2025	<input type="checkbox"/>
Decree of 21. March 1973	IT	Seals	food	01 / 2026	<input type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
Nano-free			see certificate		<input checked="" type="checkbox"/>
NSF 51	USA	Seals	food		<input checked="" type="checkbox"/>
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>
USP Chapter 87 (In vitro)	USA	Seals			<input checked="" type="checkbox"/>
USP Class VI Ch. 88 - 121 °C	USA	Seals			<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com



Material

75 Fluoroprene XP41

powder blue

cross linking: peroxidic

revision index
7

revision date
11/4/2019

page 3 / 3

No ASTM D2000 properties available

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

